

SIRIUS

**HL30
Premium
Resin**



THERMAL TRANSFER RIBBONS



TTR Properties


Base Film Thickness	5.7 ± 1.0μ
Total Thickness	8.0 ± 1.0μ
Ink Color	Black
Ink Melting Point	105°C
Maximum Print Speed	75 mm / second

Receiving Materials

Synthetics Polypropylene & Polyester
Coated Textile Labels CETUS®

Resistance

Scratch	Excellent
Chemical	Good
Alcohol	Average
Heat	Excellent
Water	Good



Dynic USA Corporation
4750 N.E. Dawson Creek Drive
Hillsboro, Oregon 97124
Phone (800) 326-1249
(503) 693-1070
Fax (503) 648-1185
www.dynic.com

Notes:

1. This chart shows Dynic USA Corporation's HL30 Premium Resin formulation on typical receiving materials.
2. Dynic USA recommends that the ribbon be tested independently to match specific label requirements, and in order to determine optimum print conditions and speed.
3. Test results may vary depending on label and printing conditions.
4. Storage: 5° to 35°C; 30 to 85% RH. Shelf Life: 1 Year.
5. Dynic USA Corporation reserves the right to change any Dynic product specifications without prior notice, provided there is no change in product performance.